

ENERGY RATINGS - CANADA

Window Style (Model)													
	Glass Options	ER	Energy Star Zone				SHGC	Visible Transmittance	Condensation Resistance	"U" Value	"U" Value	"R" Value	
A			B	C	D	(Metric) W/m²-K				(Imperial) Btu/h/ft²-°F	(Imperial)		
Single Hung Tilt #1371 CAN/CSA A440-00 Evaluation Report # 3093743-5 Air - A2/Fixed Water - B4 Structural - C3 Forced Entry - F20	DUAL LITE												
	Clear – air – clear	17					0.60	0.63	48	2.56	0.45	2.22	
	Clear – air – clear, grille	14					0.54	0.57	48	2.56	0.45	2.22	
	Clear – air – LOF (3)	30	●	●	●		0.59	0.60	54	1.93	0.34	2.94	
	Clear – air – LOF, grille	27	●	●			0.53	0.54	54	1.93	0.34	2.94	
	Clear – argon – LOF (3)	34	●	●	●	●	0.59	0.60	57	1.76	0.31	3.23	
	Clear – argon – LOF, grille	30	●	●	●		0.53	0.54	57	1.76	0.31	3.23	
	Clear – argon/krypton – LOF (3)	34	●	●	●	●	0.59	0.60	57	1.76	0.31	3.23	
	Clear – argon/krypton – LOF, grille	30	●	●	●		0.53	0.54	57	1.76	0.31	3.23	
	Bronze – air – clear	11					0.49	0.48	44	2.56	0.45	2.22	
	Bronze – air – clear, grille	8					0.44	0.43	44	2.56	0.45	2.22	
	Bronze – argon – clear	13					0.49	0.48	46	2.44	0.43	2.33	
	Bronze – argon – clear, grille	10					0.44	0.43	46	2.44	0.43	2.33	
	Bronze – argon/krypton – clear	13					0.49	0.48	46	2.44	0.43	2.33	
	Bronze – argon/krypton – clear, grille	10					0.44	0.43	46	2.44	0.43	2.33	
	Bronze – air – LOF (3)	22	●				0.45	0.44	54	1.93	0.34	2.94	
	Bronze – air – LOF, grille	19					0.40	0.39	54	1.93	0.34	2.94	
	Bronze – argon – LOF (3)	26	●	●			0.45	0.44	57	1.76	0.31	3.23	
	Bronze – argon – LOF, grille	23	●				0.40	0.39	57	1.76	0.31	3.23	
	Bronze – argon/krypton – LOF (3)	26	●	●			0.45	0.44	57	1.76	0.31	3.23	
	Bronze – argon/krypton – LOF, grille	23	●				0.40	0.39	57	1.76	0.31	3.23	
	Grey – air – clear	10					0.47	0.43	44	2.56	0.45	2.22	
	Grey – air –clear, grille	7					0.42	0.39	44	2.56	0.45	2.22	
	Grey – argon – clear	12					0.47	0.43	46	2.44	0.43	2.33	
	Grey – argon – clear, grille	9					0.42	0.39	46	2.44	0.43	2.33	
	Grey – argon/krypton – clear	12					0.47	0.43	46	2.44	0.43	2.33	
	Grey – argon/krypton – clear, grille	9					0.42	0.39	46	2.44	0.43	2.33	
	Grey – air – LOF (3)	21	●				0.43	0.40	54	1.93	0.34	2.94	
	Grey – air – LOF, grille	18	●				0.38	0.36	54	1.93	0.34	2.94	
	Grey – argon – LOF (3)	25	●	●			0.43	0.40	57	1.76	0.31	3.23	
	Grey – argon – LOF, grille	22	●				0.38	0.36	57	1.76	0.31	3.23	
	Grey – argon/krypton – LOF (3)	25	●	●			0.43	0.40	57	1.76	0.31	3.23	
	Grey – argon/krypton – LOF, grille	22	●				0.38	0.36	57	1.76	0.31	3.23	
	366 – air – clear (2)	13					0.22	0.50	56	1.76	0.31	3.23	
	366 – air – clear, grille	11					0.20	0.45	56	1.76	0.31	3.23	
	366 – argon – clear (2)	17	●	●			0.21	0.50	60	1.53	0.27	3.70	
	366 – argon – clear, grille	16	●				0.19	0.45	60	1.53	0.27	3.70	
	366 – argon/krypton – clear (2)	17	●	●			0.21	0.50	60	1.53	0.27	3.70	
	366 – argon/krypton – clear, grille	16	●				0.19	0.45	60	1.53	0.27	3.70	

ENERGY RATINGS - CANADA

Window Style (Model)												
	Glass Options	ER	Energy Star Zone				SHGC	Visible Transmittance	Condensation Resistance	"U" Value	"U" Value	"R" Value
A			B	C	D	(Metric) W/m²·K				(Imperial) Btu/h·ft²·°F	(Imperial)	
Single Hung Tilt #1371 CAN/CSA A440-00 Evaluation Report # 3093743-5 Air - A2/Fixed Water - B4 Structural - C3 Forced Entry - F20	TRIPLE LITE											
	Clear – argon – clear – argon – LOF (5)	32	●	●	●		0.54	0.55	60	1.70	0.30	3.33
	Clear – argon – LOF – argon – LOF (3&5)	35	●	●	●	●	0.51	0.52	63	1.48	0.26	3.85
	Clear – argon/krypton – clear – argon/krypton – LOF (5)	33	●	●	●		0.54	0.55	60	1.65	0.29	3.45
	Clear – argon/krypton – LOF – argon/krypton – LOF (3&5)	35	●	●	●	●	0.51	0.52	63	1.48	0.26	3.85
	Clear – krypton – clear – krypton – LOF (5)	38	●	●	●	●	0.54	0.55	63	1.42	0.25	4.00
	Clear – krypton – LOF – krypton – LOF (3&5)	40	●	●	●	●	0.51	0.52	67	1.25	0.22	4.55
	Bronze – argon – clear – argon – clear	20					0.44	0.44	55	1.99	0.35	2.86
	Bronze – argon/krypton – clear – argon/krypton – clear	21	●				0.44	0.44	56	1.93	0.34	2.94
	Bronze – krypton – clear – krypton – clear	25	●	●			0.43	0.44	58	1.76	0.31	3.23
	Bronze – argon – clear – argon – LOF (5)	25	●	●			0.40	0.40	60	1.65	0.29	3.45
	Bronze – argon/krypton – clear – argon/krypton – LOF (5)	25	●				0.40	0.40	60	1.65	0.29	3.45
	Bronze – krypton – clear – krypton – LOF (5)	30	●	●	●		0.40	0.40	63	1.42	0.25	4.00
	Bronze – argon – LOF – argon – LOF (3&5)	27	●	●			0.37	0.37	63	1.48	0.26	3.85
	Bronze – argon/krypton – LOF – argon/krypton – LOF (3&5)	29	●	●	●		0.37	0.37	64	1.42	0.25	4.00
	Bronze – krypton – LOF – krypton – LOF (3&5)	34	●	●	●	●	0.37	0.37	67	1.19	0.21	4.76
	Grey – argon – clear – argon – clear	19					0.42	0.40	55	1.99	0.35	2.86
	Grey – argon/krypton – clear – argon/krypton – clear	20					0.42	0.40	56	1.93	0.34	2.94
	Grey – krypton – clear – krypton – clear	23	●				0.41	0.40	58	1.76	0.31	3.23
	Grey – argon – clear – argon – LOF (5)	24	●				0.38	0.36	60	1.65	0.29	3.45
	Grey – argon/krypton – clear – argon/krypton – LOF (5)	24	●				0.38	0.36	60	1.65	0.29	3.45
	Grey – krypton – clear – krypton – LOF (5)	29	●	●	●		0.38	0.36	63	1.42	0.25	4.00
	Grey – argon – LOF – argon – LOF (3&5)	27	●	●			0.36	0.34	63	1.48	0.26	3.85
	Grey – argon/krypton – LOF – argon/krypton – LOF (3&5)	28	●	●	●		0.36	0.34	64	1.42	0.25	4.00
	Grey – krypton – LOF – krypton – LOF (3&5)	32	●	●	●	●	0.35	0.34	67	1.19	0.21	4.76
	366 – argon – clear – argon – clear (2)	15	●				0.20	0.46	62	1.59	0.28	3.57
	366 – argon/krypton – clear – argon/krypton – clear (2)	16	●				0.20	0.46	62	1.53	0.27	3.70
	366 – krypton – clear – krypton – clear (2)	21	●	●	●		0.20	0.46	66	1.31	0.23	4.35